



NATIONAL TESTING STANDARDS INC.
RESEARCH AND TESTING LABORATORIES

Report No. 28812

November 22, 2022

Client: Rust Bullet, LLC
300 Brinkby Ave., Suite 200
Reno, NV 89509

Reference: Mr. David Ciglar

Subject: VOC and Pigment Content of Rust Bullet Metallic Coating.

Sample Description:

One can of gray viscous liquid was submitted by the client and identified as a metallic pigmented coating.

Request:

Determine the volatile organic compound (VOC) content, the metallic pigment content (MPC) and the density of the submitted sample.

Method:

The VOC content was determined in accordance with the procedures set forth in South Coast AQMD method 304-91.

The MPC was determined in accordance with the procedures set forth in AQMD 318-95.

The density was determined as part of AQMD method 304-91.

Results:

| <u>Attribute</u> | <u>Value (g/L)</u> | <u>Required</u> |
|------------------|--------------------|-----------------|
| Density | 770.3 | n/a |
| VOC | 277.0 | 500 max. |
| MPC | 131.0 | 48 min. |

Conclusion:

The submitted sample meets the requirements of sections 232 and 301 for Sacramento Metropolitan AQMD rule 442.

NATIONAL TESTING STANDARDS

by Lewis F. West