



# RUST BULLET® DURAGRADE CONCRETE

## ENGINEERING DATA SHEET

### PRODUCT DESCRIPTION

DuraGrade Concrete is a high-performance concrete coating that can be applied directly onto concrete surfaces without any acid etching. DuraGrade Concrete is a single component urethane resistant to UV rays, acid splash and chemical solvents. Ideal for any indoor or outdoor concrete surface. Due to its UV resistance and adhesion properties, DuraGrade Concrete requires no topcoat or base/primer coat. Available in a variety of standard and custom colors. Apply by brush, roller, or spray equipment. VOC compliant in all 50 states.

### TYPICAL USES

Rust Bullet® DuraGrade Concrete provides superior protection for both indoor and outdoor concrete surfaces. Typical applications include: garage floors, patios, basement, parking structures and more. Can be used with decorative flakes. Most garage projects can be completed with two coats in just one day. Anti-skid can be added for a slip resistant surface.

### ADVANTAGES

- Easy to Apply – Ready to Use
- Does Not Require Acid Etching
- Single Component
- Outstanding Adhesion
- Excellent Resistance to Weather and Mechanical Abuse
- Excellent Chemical and Road Salt Resistance
- No Hot Tire Pickup
- Self-leveling

### SPECIFICATIONS

**Weight per gallon:** 9.5 – 9.9 lbs

**Color:** Multiple Standard and Custom

**Finish:** Glossy

**Flash Point:** 123°F

**Viscosity:** 240-300 cP

**Theoretical coverage:** Approx. 300 sq. ft./gal/coat, depending on porosity of concrete

**Solids by Volume:** 71% +/- 2%

**Recommended DFT:** Min. 6 mil; 12 mil for commercial, industrial or marine applications

**VOC Content:** 130-170 g/l (depending on color)

**Application Methods:** Brush, Roll, or Spray

**Cure Times:** Varies with relative humidity, temperature and thickness of film

- Dry-to-Recoat: 2 to 6 hours
- Dry-to-Handle: 2 to 6 hours
- Full Cure: 72 hours

**Shelf Life:** Approx. 2 years un-opened; 1 month for opened containers; Up to 6 months if sealed with Bloxygen

**Application Temp:** 35°F-110°F (2°C-43°C)

**Temperature Resistance:** Continuous: 314°F (theoretical)

**Compatibility:** With most other coatings; Always refer to the coating manufacturers guidelines for application and compatibility

**Testing:**

- Taber Abrasion (ASTM D4060): 38 mg / 1,000 Cycles
- Impact Resistance (ASTM D2794): >40 inches (exceeds max test limits)
- Mandrel Bend (ASTM D 522-13): >32% without cracking (**exceeds test**)
- Pull-off Adhesion Bond Strength (ASTM D7234-05):
  - 50mm dolly: >525 PSI (Dollies unable to be removed at ~525 max psi)
  - 20mm dolly: >1485 PSI (the concrete broke apart before DuraGrade lost adhesion)

### SAFETY INFORMATION

Avoid ingestion, inhalation and contact with skin or eyes. The use of safety glasses and nitrile gloves is recommended. When brushing, rolling or spraying, appropriate NIOSH approved respiratory protection is recommended. See [Safety Data Sheet](#) for complete safety data before use, available at [www.RustBullet.com](http://www.RustBullet.com). It is the applicator's responsibility to understand these safety precautions and the work environment, to protect themselves and/or others.

### SURFACE PREPARATION

The concrete substrate must be structurally sound and thoroughly clean and completely dry. Remove loose paint, moisture, dirt, mildew, oils, wax, loose particles, and other debris before coating. New concrete must be cured for at least 30-90 days depending on climate. Surfaces with tight existing paint or sealants or very smooth or power troweled should be sanded or ground. All repairs should be completed and allowed to fully cure prior to application. Be sure all repair materials are paintable. Adhesion and calcium chloride moisture tests should be performed and outstanding issues fixed prior to application. For more information contact us at:

**Rust Bullet, LLC ~ 300 Brinkby Avenue, Suite 200, Reno, NV 89509 USA 1(800) 245-1600, 1(775) 829-5606 [www.RustBullet.com](http://www.RustBullet.com)**

### LIMITATION OF LIABILITY

All recommendations or suggestions relating to the use of the product, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge is reliable. The product and information is designed for users having the requisite knowledge and industrial skills, and the end-user has the responsibility to determine the suitability of the product for its intended use. Conditions of use are beyond our control, Rust Bullet, LLC (the Company), disclaims any liability incurred in connection with the use of our products and information contained herein. No person is authorized or empowered to make any statement or recommendation not contained herein, any such statement or recommendation so made shall not bind The Company. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents. Rust Bullet, LLC has no control over either the quality of condition of the substrate, or the many factors affecting the use and application of the product. Therefore, Rust Bullet, LLC does not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet. The information contained in this data sheet is subject to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues. The user has the responsibility to ensure that this sheet is current prior to using the product. v103018